




## FASESCHALUNG THERMOKIEFER | CHAMFERED PROFILE THERMO-PINE



<b>Holzart   Type of wood</b>	Thermokiefer   thermally treated pine
<b>Profil   Profile</b>	Faseschalung   chamfered profile
<b>Qualität   Quality</b>	AB-VEH
<b>Dimensionen   Dimensions</b>	19x115 mm   19x144 mm
<b>Deckmaß   Face width</b>	107 mm   135 mm
<b>Dauerhaftigkeit   Durability</b>	2 (Norm DIN EN 350)
<b>Rohdichte   Wood density</b>	420 kg/m <sup>3</sup>
<b>Oberfläche   Surface</b>	gehobelt   planed
<b>Kantenbearbeitung   Edge processing</b>	abgefast   chamfered
<b>Holzfeuchtigkeit   Wood moisture</b>	Ausgleichsfeuchte ca.7%   balancing moisture apx. 7%
<b>Zertifikate   Certificates</b>	PEFC, VEH
<b>Verpackung   Packaging</b>	
<b>Verwendungshinweis   Usage note</b>	Durch den Thermoprozess verringert sich die Rohdichte um ca. 15%. Durch die verringerten Festigkeitseigenschaften ist eine Anwendung im statischen Bereich nicht möglich. Das Holz versprödet und neigt zur Absplinterung. Wie bei jeder Holzart, welche der Witterung ausgesetzt ist, entstehen vereinzelt Spannungsrisse an der Oberfläche. Dieses Verhalten ist produktspezifisch, nicht einzugrenzen und stellt keinen Reklamationsgrund dar.   The thermoprocess reduces the bulk density by approx. 15%. Due to the reduced strength properties, an application in the static area is not possible. The wood becomes brittle and tends to splinter. As with any type of wood exposed to the weather, isolated stress cracks appear on the surface. This behaviour is product-specific, cannot be limited and does not constitute grounds for complaint.